

arXiv.math AP/0603172v1 7Mar 2006. To appear in SIAM Journal on Math. Analysis 2006.

# Homogenization and field concentrations in heterogeneous media

Robert Lipton  
 Department of Mathematics,  
 Louisiana State University,  
 Baton Rouge, LA 70803

## Abstract

A multi-scale characterization of the field concentrations inside composite and polycrystalline media is developed. We focus on gradient fields associated with the intensive quantities given by the temperature and the electric potential. In the linear regime these quantities are modeled by the solution of a second order elliptic partial differential equation with oscillatory coefficients. The characteristic length scale of the heterogeneity relative to the sample size is denoted by  $\varepsilon$  and the intensive quantity is denoted by  $u^\varepsilon$ . Field concentrations are measured using the  $L^p$  norm of the gradient field  $\|\nabla u^\varepsilon\|_{L^p(D)}$  for  $2 \leq p < \infty$ . The analysis focuses on the case when  $0 < \varepsilon \ll 1$ . Explicit lower bounds on  $\liminf_{\varepsilon \rightarrow 0} \|\nabla u^\varepsilon\|_{L^p(D)}$  are developed. These bounds provide a way to rigorously assess field concentrations generated by the microgeometry without having to compute the actual field  $u^\varepsilon$ .

**Key words.** Composite materials, polycrystalline media, homogenization, field concentrations, Young measures

**AMS subject classifications.** 35B27, 74Q05

**Abbreviated title.** Homogenization and field concentrations

## 1 Introduction

The initiation of failure inside heterogeneous media is a multi-scale phenomena. Loads applied at the structural scale are often amplified by the microstructure creating local zones of high field concentration. The local amplification of the applied field creates conditions that are favorable for failure initiation [8]. This paper focuses on gradient fields associated with the intensive quantities given by the temperature and the electric potential inside heterogeneous media. The local integrability of the gradient directly correlates with singularity strength which influences the onset of failure such as dielectric breakdown.

In this work it is shown how to assess the  $L^p$  integrability of the gradient fields in microstructured media by investigating the multi-scale integrability of suitably defined quantities. The analysis is carried out with minimal regularity assumptions on the coefficients describing the local properties inside the heterogeneous media. The results are described in

terms of the  $p^{th}$  order moments of the solution of two-scale corrector problems. The quantities are sensitive to microscopic field concentrations and can become divergent for  $p > 2$ . This is in contrast to the well known effective constitutive properties which are based upon local averages and are bounded above independently of the microgeometry.

The results given here are presented in the context of two-scale homogenization [1], [18]. We consider a bounded domain  $\Omega$  in  $\mathbf{R}^n$ ,  $n \geq 2$ . A common microstructure that admits a two-scale description is a simple generalization of a uniformly periodic microstructure and is described as follows. Consider a partition of the domain  $\Omega$  made up of measurable subsets  $\Omega_\ell$ ,  $\ell = 1, 2, \dots, K$  such that  $\Omega = \cup_{\ell=1}^K \Omega_\ell$ . Inside each subdomain  $\Omega_\ell$  we place a different periodic microstructure made from  $N$  anisotropic heat conductors. This type of microstructure will be referred to as a piecewise periodic microstructure. Well known engineering composites that are modeled by piecewise periodic microstructures include fiber reinforced laminates [6], [19] and [21].

The thermal conductivity tensor for the piecewise periodic microstructure is described as follows. The indicator function for each of the subdomains  $\Omega_\ell$  is denoted by  $\chi_{\Omega_\ell}(\mathbf{x})$ , taking the value 1 for points in  $\Omega_\ell$  and zero outside. In order to describe the periodic microstructure inside the  $\ell^{th}$  subdomain we introduce the unit period cell  $Q$ . The configuration of the  $N$  phases inside  $Q$  is described by the indicator functions  $\chi_\ell^i(\mathbf{y})$ ,  $i = 1, \dots, N$  associated with each phase. Here  $\chi_\ell^i(\mathbf{y}) = 1$  for points inside the  $i^{th}$  phase and zero outside. The length scale of the microstructure relative to the size of the domain  $\Omega$  is given by  $\varepsilon_k = 1/k$ ,  $k = 1, 2, \dots$ . The microstructure is obtained by rescaling the configuration inside the unit period cell. The indicator function of the  $i^{th}$  conductor in the microstructured composite is given by

$$\chi_i^{\varepsilon_k}(\mathbf{x}) = \chi_i(\mathbf{x}, \mathbf{x}/\varepsilon_k) = \sum_{\ell}^K \chi_{\Omega_\ell}(\mathbf{x}) \chi_\ell^i(\mathbf{x}/\varepsilon_k). \quad (1.1)$$

The local conductivity tensor  $A^{\varepsilon_k}$  has a two-scale structure and is given by

$$A^{\varepsilon_k}(\mathbf{x}) = A(\mathbf{x}, \mathbf{x}/\varepsilon_k) = \sum_i^N A^i \chi_i(\mathbf{x}, \mathbf{x}/\varepsilon_k). \quad (1.2)$$

Other heterogeneous media that are amenable to similar or more general two-scale descriptions include polycrystalline materials such as metals and ceramics. We state the general hypotheses under which the two-scale homogenization theory applies, see [1] and [2]. It is assumed that  $A(\mathbf{x}, \mathbf{y})$  is a matrix defined on  $\Omega \times Q$  and there exist positive numbers  $\alpha < \beta$  such that for every vector  $\eta$  in  $\mathbf{R}^n$  that

$$\alpha|\eta|^2 \leq A(\mathbf{x}, \mathbf{y})\eta \cdot \eta \leq \beta|\eta|^2. \quad (1.3)$$

The conductivity  $A_{ij}(\mathbf{x}, \mathbf{y})$  is  $Q$ -periodic in the second variable,  $A_{ij}(\mathbf{x}, \mathbf{x}/\varepsilon_k)$  is measurable, satisfies

$$\lim_{\varepsilon_k \rightarrow 0} \int_{\Omega} \left| A_{ij}(\mathbf{x}, \frac{\mathbf{x}}{\varepsilon_k}) \right|^2 d\mathbf{x} = \int_{\Omega \times Q} |A_{ij}(\mathbf{x}, \mathbf{y})|^2 d\mathbf{x}d\mathbf{y} \quad (1.4)$$

and for any suitable two scale trial field  $\psi(\mathbf{x}, \mathbf{y})$

$$\lim_{\varepsilon_k \rightarrow 0} \int_{\Omega} A_{ij}(\mathbf{x}, \frac{\mathbf{x}}{\varepsilon_k}) \psi(\mathbf{x}, \mathbf{x}/\varepsilon_k) d\mathbf{x} = \int_{\Omega \times Q} A_{ij}(\mathbf{x}, \mathbf{y}) \psi(\mathbf{x}, \mathbf{y}) d\mathbf{x}d\mathbf{y}. \quad (1.5)$$

The convergence given by (1.5) is a weak convergence and is known as two-scale convergence [1] [18]. The space of suitable two-scale trials is denoted by  $L^2[D; C_{per}(Q)]$ . Here  $C_{per}(Q)$  denotes  $Q$ -periodic continuous functions defined on  $\mathbf{R}^3$  and the space  $L^2[D; C_{per}(Q)]$  is the space of functions  $h : \Omega \rightarrow C_{per}(Q)$  which are measurable and satisfy  $\int_{\Omega} \|h(\mathbf{x})\|_{C_{per}(Q)}^2 d\mathbf{x} < \infty$ . The norm  $\|h(\mathbf{x})\|_{C_{per}(Q)}$  is defined by  $\sup_{\mathbf{y} \in Q} |h(\mathbf{x}, \mathbf{y})|$ . In what follows no other regularity hypothesis on the conductivity matrix  $A(\mathbf{x}, \mathbf{y})$  is made.

The temperature field  $u^{\varepsilon_k}$  associated with the conductivity tensor field  $A^{\varepsilon_k}(\mathbf{x}) = A(\mathbf{x}, \mathbf{x}/\varepsilon_k)$  is the solution of the equilibrium equation

$$-\operatorname{div} (A^{\varepsilon_k}(\mathbf{x}) \nabla u^{\varepsilon_k}) = f \quad \text{in } \Omega \quad (1.6)$$

with the boundary conditions given by  $u^{\varepsilon_k} = 0$  on  $\partial\Omega_D$  and  $\mathbf{n} \cdot A^{\varepsilon_k} \nabla u^{\varepsilon_k} = g$  on  $\partial\Omega_N$  with  $\partial\Omega_D \cap \partial\Omega_N = \emptyset$  and  $\partial\Omega = \overline{\partial\Omega_D} \cup \overline{\partial\Omega_N}$ .

In what follows we consider the limit as  $\varepsilon_k$  tends to zero. We fix a subdomain  $D$  of  $\Omega$  and derive lower bounds on

$$\liminf_{\varepsilon_k \rightarrow 0} \|\nabla u^{\varepsilon_k}\|_{L^p(D)}. \quad (1.7)$$

The lower bound is expressed in terms of a two-scale integral that encodes the field amplification properties of the microstructure. It is formulated in terms of the solution of the homogenized problem together with a local corrector matrix that captures the interaction between the periodic microstructure and the gradients of the homogenized temperature field. The bounds introduced here provide a rigorous way to assess field concentrations generated by the microgeometry without having to compute the full solution  $u^{\varepsilon_k}$ .

We consider an orthonormal basis for  $\mathbf{R}^n$  and denote the basis vectors by  $\mathbf{e}^i$ ,  $i = 1, \dots, n$ . The lower bound is given in terms of the solutions  $w^i(\mathbf{x}, \mathbf{y})$  to the local periodic problem. For each  $\mathbf{x}$  in  $\Omega$  the function  $w^i(\mathbf{x}, \mathbf{y})$  is a  $Q$  periodic function of the second variable  $\mathbf{y}$  and is a solution of

$$\operatorname{div}_{\mathbf{y}} (A(\mathbf{x}, \mathbf{y}) (\nabla_{\mathbf{y}} w^i(\mathbf{x}, \mathbf{y}) + \mathbf{e}^i)) = 0, \quad (1.8)$$

with  $\int_Q w^i(\mathbf{x}, \mathbf{y}) d\mathbf{y} = 0$ . The corrector matrix  $P(\mathbf{x}, \mathbf{y})$  is defined by

$$P_{ij}(\mathbf{x}, \mathbf{y}) = \partial_{y_j} w^i(\mathbf{x}, \mathbf{y}) + \delta_{ij}, \quad (1.9)$$

where  $\delta_{ij} = 1$  for  $i = j$  and zero otherwise. The associated effective conductivity tensor  $A^E(\mathbf{x})$  is given by

$$A^E(\mathbf{x}) = \int_Q A(\mathbf{x}, \mathbf{y}) P(\mathbf{x}, \mathbf{y}) d\mathbf{y}. \quad (1.10)$$

The two-scale homogenization theory gives the following theorem [1].

**Theorem 1.1.** Two-scale Homogenization Theorem

*The sequence of solutions  $\{u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  of (1.6) converges weakly to  $u^H(\mathbf{x})$  in  $H^1(\Omega)$  where  $u^H$  is the solution of the homogenized problem*

$$\begin{aligned} -\operatorname{div} (A^E(\mathbf{x}) \nabla u^H(\mathbf{x})) &= f(\mathbf{x}), \quad \text{in } \Omega, \\ u^H(\mathbf{x}) &= 0, \quad \text{on } \partial\Omega_D, \quad \text{and} \\ \mathbf{n} \cdot A^E \nabla u^H &= g, \quad \text{on } \partial\Omega_N. \end{aligned} \quad (1.11)$$

The field concentration functions of order  $p$  are defined by

$$f_p(\mathbf{x}, \nabla u^H(\mathbf{x})) \equiv \left( \int_Q |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} \right)^{1/p}, \quad 2 \leq p \leq \infty \quad (1.12)$$

and  $f_p(\mathbf{x}, \nabla u^H(\mathbf{x})) \leq f_q(\mathbf{x}, \nabla u^H(\mathbf{x}))$  for  $p \leq q$ . It is clear that  $f_p$  corresponds to a  $p^{\text{th}}$  order moment of the corrector matrix (1.9) and

$$f_\infty(\mathbf{x}, \nabla u^H(\mathbf{x})) \equiv \lim_{p \rightarrow \infty} \left( \int_Q |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} \right)^{1/p}. \quad (1.13)$$

**Theorem 1.2.** Lower Bounds on Field Concentrations

For  $2 \leq p < \infty$

$$\left( \int_D (f_p(\mathbf{x}, \nabla u^H(\mathbf{x})))^p d\mathbf{x} \right)^{1/p} \leq \liminf_{\varepsilon_k \rightarrow 0} \|\nabla u^{\varepsilon_k}\|_{L^p(D)}. \quad (1.14)$$

For multi-phase conductivity problems with coefficients described by (1.2) the field concentration functions of order  $p$  are defined for each phase and are given by

$$f_p^i(\mathbf{x}, \nabla u^H(\mathbf{x})) \equiv \left( \int_Q \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} \right)^{1/p}, \quad i = 1, \dots, N, \quad 2 \leq p \leq \infty \quad (1.15)$$

and  $f_p^i(\mathbf{x}, \nabla u^H(\mathbf{x})) \leq f_q^i(\mathbf{x}, \nabla u^H(\mathbf{x}))$  for  $p \leq q$ . As before one defines

$$f_\infty^i(\mathbf{x}, \nabla u^H(\mathbf{x})) \equiv \lim_{p \rightarrow \infty} \left( \int_Q \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} \right)^{1/p}. \quad (1.16)$$

For this case lower bounds on

$$\liminf_{\varepsilon_k \rightarrow 0} \|\chi_i^{\varepsilon_k} \nabla u^{\varepsilon_k}\|_{L^p(D)} \quad (1.17)$$

are given by the following theorem.

**Theorem 1.3.** Lower Bounds for Multi-phase Composites

For  $2 \leq p < \infty$

$$\left( \int_D (f_p^i(\mathbf{x}, \nabla u^H(\mathbf{x})))^p d\mathbf{x} \right)^{1/p} \leq \liminf_{\varepsilon_k \rightarrow 0} \|\chi_i^{\varepsilon_k} \nabla u^{\varepsilon_k}\|_{L^p(D)}. \quad (1.18)$$

The bounds can be applied to develop a Chebyshev Inequality for the distribution functions associated with the sequence  $\{\chi_i^{\varepsilon_k} |\nabla u^{\varepsilon_k}|\}_{\varepsilon_k > 0}$ . Here the distribution function  $\lambda_i^{\varepsilon_k}(D, t)$  gives the measure of the set inside  $D$  where  $\chi_i^{\varepsilon_k} |\nabla u^{\varepsilon_k}| > t$ .

Arguing as in Proposition 2.1 of [12] and combining with (1.18) gives the following

**Theorem 1.4.** Homogenized Chebyshev Inequality

$$\limsup_{\varepsilon_k \rightarrow 0} \lambda_i^{\varepsilon_k}(D, t) \leq t^{-p} \left( \int_D (f_p^i(\mathbf{x}, \nabla u^H(\mathbf{x})))^p d\mathbf{x} \right) \leq t^{-p} \liminf_{\varepsilon_k \rightarrow 0} \|\chi_i^{\varepsilon_k} \nabla u^{\varepsilon_k}\|_{L^p(D)}^p. \quad (1.19)$$

It is pointed out that Theorems 1.2 and 1.3 are obtained using the minimum regularity assumptions on the coefficients  $A^{\varepsilon_k}$ . Because of this the hypotheses of (Theorem 2.6, [1]) do not apply and one can not take advantage of the strong convergence given in that Theorem. Instead the theorems are proved using a perturbation approach introduced in [11], [13], see Section 2.

The lower bounds are sensitive to the presence of singularities generated by the microstructure. To illustrate this we consider a microstructure made from a periodic distribution of uniaxial crystallites embedded in an isotropic matrix of unit conductivity. The period cell for the composite is illustrated in Figure 1. Each crystallite occupies a sphere and has conductivity  $\lambda_1$  in the radial direction and  $\lambda_2$  in the tangential direction. The dispersion of the  $N$  crystallites is specified by  $\cup_{\ell}^N B(\mathbf{y}^{\ell}, r_{\ell})$  where  $B(\mathbf{y}^{\ell}, r_{\ell})$  denotes the  $\ell^{\text{th}}$  sphere centered at  $\mathbf{y}^{\ell}$  with radius  $r_{\ell}$ . Each crystallite has a conductivity tensor given by

$$A(\mathbf{y}) = \lambda_1 \mathbf{n} \otimes \mathbf{n} + \lambda_2 (I - \mathbf{n} \otimes \mathbf{n}), \quad (1.20)$$

where  $\mathbf{n} = (\mathbf{y} - \mathbf{y}^{\ell})/|\mathbf{y} - \mathbf{y}^{\ell}|$  for  $\mathbf{y}$  in  $B(\mathbf{y}^{\ell}, r_{\ell})$  and  $I$  is the  $3 \times 3$  identity. Outside the crystallites we set  $A(\mathbf{y}) = I$ . It is supposed that the aggregate of crystallites occupy an area fraction  $0 < \theta < 1$  of the unit period cell. It is noted that the conductivity inside each crystallite is precisely the one employed in the Schulgasser sphere assemblage [22].

When a constant gradient field is applied to a single isolated crystallite and  $\lambda_1 > \lambda_2$  the crystallite exhibits a gradient field singularity at its center. In what follows we use the lower bound (1.14) to show how this local information effects the integrability of the sequence  $\{\nabla u^{\varepsilon_k}\}_{\varepsilon_k > 0}$ . We form  $A^{\varepsilon_k} = A(\mathbf{x}/\varepsilon_k)$  and consider solutions  $u^{\varepsilon_k}$  of (1.6). To fix ideas we choose  $f$  to be in  $L^r(\Omega)$  for  $r > 3$  and  $g$  to be in  $L^2(\partial\Omega_N)$ . In what follows  $\lambda_2$  is restricted to lie in the interval  $1/2 < \lambda_2 < 1$  and  $\lambda_1 = 1/(2\lambda_2 - 1)$ . For this choice it is shown in Section 3 that the homogenized temperature field  $u^H$  is the solution of (1.11) with  $A^E = I$ .

For  $D$  compactly contained in  $\Omega$  it follows from the  $L^p$  theory [15], that  $\|\nabla u^H\|_{L^p(D)} < \infty$  for every  $1 \leq p < \infty$ . On the other hand calculation and application of Theorem 1.2 shows that

$$LB(p) \times \|\nabla u^H\|_{L^p(D)} \leq \liminf_{\varepsilon_k \rightarrow 0} \|\nabla u^{\varepsilon_k}\|_{L^p(D)}, \quad (1.21)$$

where

$$LB(p) = \begin{cases} \frac{3p\theta(2\lambda_2-1)}{2(1-\lambda_2)(\frac{3}{2(1-\lambda_2)}-p)} + (1-\theta), & \text{for, } p < \frac{3}{2(1-\lambda_2)}, \\ +\infty, & \text{for, } p \geq \frac{3}{2(1-\lambda_2)}. \end{cases} \quad (1.22)$$

For a fixed choice of  $\lambda_2$  the value  $p_c = \frac{3}{2(1-\lambda_2)}$  satisfies  $3 < p_c < +\infty$  and

$$\liminf_{\varepsilon_k \rightarrow 0} \|\nabla u^{\varepsilon_k}\|_{L^p(D)} = +\infty, \text{ for } p \geq p_c. \quad (1.23)$$

This is in stark contrast to the  $L^p$  integrability of the the gradient of the homogenized solution which holds for any  $p < +\infty$ . It is clear for this example that the information carried by the homogenized problem is not adequate and misses the singular behavior exhibited by the sequence  $\{\nabla u^{\varepsilon_k}\}_{\varepsilon_k > 0}$ . This example shows that failure initiation criteria based solely upon the solution of the homogenized equations will be optimistic. The inequalities given above are established in Section 3.

The maximum integrability exponent for the gradient of the solution of the local problem (1.8) is referred to as the threshold exponent for the composite. The threshold exponent is introduced in the work of Milton [16] and measures the worst singularity of the gradient field. The threshold exponent is precisely  $p_c$  for the local problem considered here and corresponds to the divergence in the lower bound for  $p \geq p_c$ .




Figure 1: Unit period cell with Schulgasser crystallites embedded inside a material with unit thermal conductivity.

Next we consider an example for which the sequence  $\{\nabla u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  is uniformly bounded in  $L^p$  for some class of coefficients and right hand sides  $f$ . For this case we show that the lower bound given in Theorem 1.2 is attained. In this example we make use of the a priori estimates for  $\{\nabla u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  developed in the Theorem 4 of Avellaneda and Lin [3]. Let  $\Omega$  be a  $C^{1,\alpha}$  domain ( $0 < \alpha \leq 1$ ) and suppose for  $0 < \gamma \leq 1$ ,  $C > 0$ , that  $A(\mathbf{y}) \in C^\gamma(\mathbf{R}^n)$  and  $\|A(\mathbf{y})\|_{C^\gamma(\mathbf{R}^n)} \leq C$ . Then we choose  $A^{\varepsilon_k} = A(\mathbf{x}/\varepsilon_k)$ . For  $\delta > 0$  suppose  $2 \leq q \leq n + \delta$  and  $f \in L^q$  and set  $1/\hat{q} = 1/q - 1/(n + \delta)$ . Given these choices we consider the  $W_0^{1,2}(\Omega)$  solutions  $u^{\varepsilon_k}$  of

$$-\operatorname{div} (A^{\varepsilon_k}(\mathbf{x})\nabla u^{\varepsilon_k}) = f \text{ in } \Omega. \quad (1.24)$$

It is shown in Section 4 that (1.14) holds with equality for every  $p$  such that  $p < \hat{q}$ . In fact it is seen more generally that for  $p < \hat{q}$  and any Caratheodory function  $\psi : D \times \mathbf{R}^n \rightarrow \mathbf{R}$

satisfying

$$|\psi(\mathbf{x}, \eta)| \leq |\eta|^p, \text{ for a.e. } \mathbf{x} \in D \text{ and } \eta \in \mathbf{R}^3, \quad (1.25)$$

that

$$\lim_{\varepsilon_k \rightarrow 0} \int_D \psi(\mathbf{x}, \nabla u^{\varepsilon_k}(\mathbf{x})) d\mathbf{x} = \int_D \int_Q \psi(\mathbf{x}, P(\mathbf{y}) \nabla u^H(\mathbf{x})) d\mathbf{y} d\mathbf{x}. \quad (1.26)$$

This is established in Section 4.

It is anticipated that there are several classes of conductivity coefficients and right hand sides  $f$  for which the lower bounds are attained. In this direction we point out the a priori estimates given in [7], [9], [10] and [23].

We conclude noting that the analogues of the field concentration functions (1.12) and (1.15) have appeared earlier in the contexts of G-convergence and random media, see [11] and [12]. In those treatments they are shown to provide upper bounds for the distribution function of the local stress and electric field for G-convergent sequences of elasticity tensors and random dielectric tensors.

## 2 Derivation of the lower bounds

We recall the weak formulation of the  $\varepsilon_k > 0$  problem given by (1.6). Let  $V$  denote the closure in  $H^1(\Omega)$  of all smooth functions that vanish on  $\partial\Omega_D$ . We suppose that  $f$  is in  $L^2(\Omega)$  and  $g$  belongs to  $L^2(\partial\Omega_N)$ . The function  $u^{\varepsilon_k}$  belonging to  $V$  is the solution of the weak formulation of the boundary value problem given by

$$\int_{\Omega} A(\mathbf{x}, \mathbf{x}/\varepsilon_k) \nabla u^{\varepsilon_k} \cdot \nabla \varphi d\mathbf{x} = \int_{\Omega} f \varphi d\mathbf{x} + \int_{\partial\Omega_N} g \varphi ds, \quad (2.1)$$

for every  $\varphi$  in  $V$ . Here  $ds$  is an element of surface area.

In order to express the two-scale weak formulation of (1.11) we introduce the following function spaces. The space of square integrable  $Q$ -periodic mean zero functions with square integrable derivatives is denoted by  $H_{per}^1(Q)/\mathbf{R}$ . The norm of an element  $v$  in this space is denoted by  $\|v\|_{H_{per}^1(Q)/\mathbf{R}}$ . The space of measurable functions  $h$  from  $\Omega$  to  $H_{per}^1(Q)/\mathbf{R}$  for which  $\int_{\Omega} \|h(\mathbf{x})\|_{H_{per}^1(Q)/\mathbf{R}}^2 d\mathbf{x} < \infty$  is denoted by  $L^2[\Omega; H_{per}^1(Q)/\mathbf{R}]$ . This function space was introduced for the description of the two-scale homogenized problem in [18]. The weak formulation of the two-scale homogenized problem (1.11) is given by the unfolded variational principle [1], [5], [14].

### Theorem 2.1. Unfolded Variational Principle

*The pair  $(u^H, u_1)$  is the unique solution in  $V \times L^2[\Omega; H_{per}^1(Q)/\mathbf{R}]$  of*

$$\begin{aligned} & \int_{\Omega} \int_Q A(\mathbf{x}, \mathbf{y}) (\nabla u^H(\mathbf{x}) + \nabla_{\mathbf{y}} u_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla \varphi(\mathbf{x}) + \nabla_{\mathbf{y}} \varphi_1(\mathbf{x}, \mathbf{y})) d\mathbf{y} d\mathbf{x} \\ & = \int_{\Omega} f \varphi d\mathbf{x} + \int_{\partial\Omega_N} g \varphi ds, \end{aligned} \quad (2.2)$$

for every  $(\varphi, \varphi_1)$  in  $V \times L^2[\Omega; H_{per}^1(Q)/\mathbf{R}]$ . Moreover

$$\nabla u^H + \nabla_{\mathbf{y}} u_1(\mathbf{x}, \mathbf{y}) = P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x}). \quad (2.3)$$

In order to establish Theorems 1.2 and 1.3 we recall the function spaces used in the description of two-scale convergence [14]. The space  $C_{per}(Q)$  denotes  $Q$ -periodic continuous functions defined on  $\mathbf{R}^3$ . For  $1 \leq r < \infty$  the space  $L^r[D; C_{per}(Q)]$  is the space of functions  $h : D \rightarrow C_{per}(Q)$  which are measurable and satisfy  $\int_D \|h(\mathbf{x})\|_{C_{per}(Q)}^r d\mathbf{x} < \infty$ . Here  $\|h(\mathbf{x})\|_{C_{per}(Q)} = \sup_{\mathbf{y} \in Q} |h(\mathbf{x}, \mathbf{y})|$ . The intersection of the spaces  $L^\infty(D \times Q)$  and  $L^r[D; C_{per}(Q)]$  is denoted by  $V^r$ . For  $1 < r < \infty$  we introduce  $1 < r' < \infty$  such that  $\frac{1}{r} + \frac{1}{r'} = 1$ . We establish Theorems 1.2 and 1.3 with the aid of the following Lemmas.

**Lemma 2.1.** Localization Lemma

Fix a domain of interest  $D$  inside  $\Omega$ . Let  $q(\mathbf{x}, \mathbf{y})$  be any test function in  $V^r$  then one can pass to the limit  $\varepsilon_k \rightarrow 0$  in the sequence of solutions  $\{u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  of (1.6) to obtain:

$$\lim_{\varepsilon_k \rightarrow 0} \int_D q(\mathbf{x}, \mathbf{x}/\varepsilon_k) |\nabla u^{\varepsilon_k}|^2 d\mathbf{x} = \int_D \int_Q q(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^2 d\mathbf{y} d\mathbf{x}. \quad (2.4)$$

For multi-phase composites with coefficients described by (1.2) we restrict attention inside each phase and state the following lemma.

**Lemma 2.2.** Localization Lemma in Multi-phase Composites

Let  $q(\mathbf{x}, \mathbf{y})$  be any test function in  $V^r$  then one can pass to the limit  $\varepsilon_k \rightarrow 0$  in the sequence of solutions  $\{u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  of (1.6) to obtain:

$$\begin{aligned} & \lim_{\varepsilon_k \rightarrow 0} \int_D q(\mathbf{x}, \mathbf{x}/\varepsilon_k) \chi_i^{\varepsilon_k}(\mathbf{x}) |\nabla u^{\varepsilon_k}|^2 d\mathbf{x} \\ &= \int_D \int_Q q(\mathbf{x}, \mathbf{y}) \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^2 d\mathbf{y} d\mathbf{x}. \end{aligned} \quad (2.5)$$

The proofs of Lemmas 2.1 and 2.2 are given at the end of this section.

To illustrate the ideas we use Lemma 2.2 to establish Theorem 1.3 noting that Theorem 1.2 follows from Lemma 2.1 in the same way.

**Proof of Theorem 1.3.** For each  $\varepsilon_k > 0$  we apply Hölder's inequality to the left side of (2.5) to obtain

$$\begin{aligned} & \int_D \int_Q q(\mathbf{x}, \mathbf{y}) \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^2 d\mathbf{y} d\mathbf{x} \\ & \leq \lim_{\varepsilon_k \rightarrow 0} \left( \int_D |q(\mathbf{x}, \mathbf{x}/\varepsilon_k)|^r dx \right)^{1/r} \liminf_{\varepsilon_k \rightarrow 0} \left( \int_D \chi_i^{\varepsilon_k}(\mathbf{x}) |\nabla u^{\varepsilon_k}|^{2r'} d\mathbf{x} \right)^{1/r'}. \end{aligned} \quad (2.6)$$

Noting [14] that

$$\lim_{\varepsilon_k \rightarrow 0} \left( \int_D |q(\mathbf{x}, \mathbf{x}/\varepsilon_k)|^r dx \right)^{1/r} = \left( \int_D \int_Q |q(\mathbf{x}, \mathbf{y})|^r dy dx \right)^{1/r} \equiv \|q(\mathbf{x}, \mathbf{y})\|_{L^r(D \times Q)} \quad (2.7)$$

we obtain

$$\frac{\int_D \int_Q q(\mathbf{x}, \mathbf{y}) \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^2 dy dx}{\|q(\mathbf{x}, \mathbf{y})\|_{L^r(D \times Q)}} \leq \liminf_{\varepsilon_k \rightarrow 0} \left( \int_D \chi_i^{\varepsilon_k}(\mathbf{x}) |\nabla u^{\varepsilon_k}|^{2r'} d\mathbf{x} \right)^{1/r'} \quad (2.8)$$

Since  $V^r$  is dense in  $L^r(D \times Q)$  we substitute an approximation of  $\chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^{2r'-2}$  for  $q$  in (2.8) to find that

$$\left( \int_D \int_Q \chi_i(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^{2r'} dy dx \right)^{1/r'} \leq \liminf_{\varepsilon_k \rightarrow 0} \left( \int_D \chi_i^{\varepsilon_k}(\mathbf{x}) |\nabla u^{\varepsilon_k}|^{2r'} d\mathbf{x} \right)^{1/r'} \quad (2.9)$$

Theorem 1.3 follows for  $2 < p < \infty$  upon taking the square root on both sides of (2.9). The case  $p = 2$  follows immediately upon choosing  $q(\mathbf{x}, \mathbf{y}) = 1$  in Lemma 2.2.

We conclude by providing the proof of Lemma 2.2 and note that the proof of Lemma 2.1 is identical.

**Proof of Lemma 2.2.** The indicator function of the set of interest  $D$  is denoted by  $\chi_D(\mathbf{x})$ . We choose a test function  $q(\mathbf{x}, \mathbf{y})$  in  $V^r$  and set  $p(\mathbf{x}, \mathbf{y}) = \chi_D(\mathbf{x}) \chi_i(\mathbf{x}, \mathbf{y}) q(\mathbf{x}, \mathbf{y})$ . For  $\delta\beta > 0$  we form the perturbed conductivity tensor  $\tilde{A}_{ij}(\mathbf{x}, \mathbf{y}) = A_{ij}(\mathbf{x}, \mathbf{y}) + \delta\beta p(\mathbf{x}, \mathbf{y}) \delta_{ij}$ . We choose  $\delta\beta$  sufficiently small so that  $\tilde{A}(\mathbf{x}, \mathbf{y})$  satisfies (1.3). By construction  $\tilde{A}(\mathbf{x}, \mathbf{x}/\varepsilon_k)$  is measurable and satisfies (1.4) and (1.5). Consider the associated solution  $\tilde{u}^{\varepsilon_k}$  in  $V$  of the weak formulation of the boundary value problem given by

$$\int_{\Omega} \tilde{A}(\mathbf{x}, \mathbf{x}/\varepsilon_k) \nabla \tilde{u}^{\varepsilon_k} \cdot \nabla \varphi d\mathbf{x} = \int_{\Omega} f \varphi d\mathbf{x} + \int_{\partial\Omega_N} g \varphi ds, \quad \text{for every } \varphi \text{ in } V. \quad (2.10)$$

Set  $\tilde{u}^{\varepsilon_k} = u^{\varepsilon_k} + \delta u^{\varepsilon_k}$  and subtraction of (2.1) from (2.10) gives

$$\int_{\Omega} \tilde{A}(\mathbf{x}, \mathbf{x}/\varepsilon_k) \nabla \delta u^{\varepsilon_k} \cdot \nabla \varphi d\mathbf{x} + \int_{\Omega} \delta\beta p(\mathbf{x}, \mathbf{x}/\varepsilon_k) \nabla u^{\varepsilon_k} \cdot \nabla \varphi d\mathbf{x} = 0. \quad (2.11)$$

Choosing  $\varphi = u^{\varepsilon_k}$  in (2.11) and application of the identity

$$\int_{\Omega} A(\mathbf{x}, \mathbf{x}/\varepsilon_k) \nabla u^{\varepsilon_k} \cdot \nabla \delta u^{\varepsilon_k} d\mathbf{x} = \int_{\Omega} f \delta u^{\varepsilon_k} d\mathbf{x} + \int_{\partial\Omega_N} g \delta u^{\varepsilon_k} ds, \quad (2.12)$$

gives

$$\delta\beta \times \int_{\Omega} p(\mathbf{x}, \mathbf{x}/\varepsilon_k) |\nabla u^{\varepsilon_k}|^2 d\mathbf{x} + T^{\varepsilon_k} = - \int_{\Omega} f \delta u^{\varepsilon_k} d\mathbf{x} - \int_{\partial\Omega_N} g \delta u^{\varepsilon_k} ds, \quad (2.13)$$

where

$$T^{\varepsilon_k} = \delta\beta \times \int_{\Omega} p(\mathbf{x}, \mathbf{x}/\varepsilon_k) (\nabla \delta u^{\varepsilon_k}) \cdot \nabla u^{\varepsilon_k} d\mathbf{x}. \quad (2.14)$$

Next set  $\varphi = \delta u^{\varepsilon_k}$  in (2.11) and it follows from Cauchy's inequality and (1.3) that

$$\|\nabla \delta u^{\varepsilon_k}\|_{L^2(\Omega)} \leq C\delta\beta, \quad (2.15)$$

where here and throughout  $C$  denotes a generic constant independent of  $\varepsilon_k$ . From this it is evident that

$$|T^{\varepsilon_k}| < C\delta\beta^2. \quad (2.16)$$

Next we pass to the  $\varepsilon_k \rightarrow 0$  limit and apply Theorems 1.1 and 2.1 to find that the sequence  $\{\tilde{u}^{\varepsilon_k}\}_{\varepsilon_k > 0}$  converges weakly in  $H^1(\Omega)$  to  $\tilde{u}^H$ , where  $(\tilde{u}^H, \tilde{u}_1)$  is the solution in  $V \times L^2[\Omega; H_{per}^1(Q)/\mathbf{R}]$  of

$$\begin{aligned} & \int_{\Omega} \int_Q \tilde{A}(\mathbf{x}, \mathbf{y}) (\nabla \tilde{u}^H(\mathbf{x}) + \nabla_{\mathbf{y}} \tilde{u}_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla \varphi(\mathbf{x}) + \nabla_{\mathbf{y}} \varphi_1(\mathbf{x}, \mathbf{y})) \, d\mathbf{y} \, d\mathbf{x} \\ &= \int_{\Omega} f\varphi \, d\mathbf{x} + \int_{\partial\Omega_N} g\varphi \, ds, \end{aligned} \quad (2.17)$$

for every  $(\varphi, \varphi_1)$  in  $V \times L^2[\Omega; H_{per}^1(Q)/\mathbf{R}]$ . Set  $\tilde{u}^H - u^H = \delta u^H$ ,  $\tilde{u}_1 - u_1 = \delta u_1$  and subtraction of (2.2) from (2.17) gives

$$\begin{aligned} & \int_{\Omega} \int_Q \tilde{A}(\mathbf{x}, \mathbf{y}) (\nabla \delta u^H(\mathbf{x}) + \nabla_{\mathbf{y}} \delta u_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla \varphi(\mathbf{x}) + \nabla_{\mathbf{y}} \varphi_1(\mathbf{x}, \mathbf{y})) \, d\mathbf{y} \, d\mathbf{x} \\ &+ \int_{\Omega} \int_Q \delta\beta p(\mathbf{x}, \mathbf{y}) (\nabla u^H(\mathbf{x}) + \nabla_{\mathbf{y}} u_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla \varphi(\mathbf{x}) + \nabla_{\mathbf{y}} \varphi_1(\mathbf{x}, \mathbf{y})) \, d\mathbf{y} \, d\mathbf{x} = 0. \end{aligned} \quad (2.18)$$

Choosing  $(\varphi, \varphi_1) = (u^H, u_1)$  in (2.18) together with the identity

$$\begin{aligned} & \int_{\Omega} \int_Q A(\mathbf{x}, \mathbf{y}) (\nabla u^H(\mathbf{x}) + \nabla_{\mathbf{y}} u_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla \delta u^H(\mathbf{x}) + \nabla_{\mathbf{y}} \delta u_1(\mathbf{x}, \mathbf{y})) \, d\mathbf{y} \, d\mathbf{x} \\ &= \int_{\Omega} f\delta u^H \, d\mathbf{x} + \int_{\partial\Omega_N} g\delta u^H \, ds. \end{aligned} \quad (2.19)$$

gives

$$\begin{aligned} & \delta\beta \times \int_{\Omega} \int_Q p(\mathbf{x}, \mathbf{y}) |P(\mathbf{x}, \mathbf{y}) \nabla u^H(\mathbf{x})|^2 \, d\mathbf{y} \, d\mathbf{x} + \tilde{T} \\ &= - \int_{\Omega} f\delta u^H \, d\mathbf{x} - \int_{\partial\Omega_N} g\delta u^H \, ds, \end{aligned} \quad (2.20)$$

where

$$\tilde{T} = \delta\beta \times \int_{\Omega} \int_Q p(\mathbf{x}, \mathbf{y}) (\nabla \delta u^H + \nabla_{\mathbf{y}} \delta u_1(\mathbf{x}, \mathbf{y})) \cdot (\nabla u^H + \nabla_{\mathbf{y}} u_1(\mathbf{x}, \mathbf{y})) \, d\mathbf{x}. \quad (2.21)$$

Next set  $(\varphi, \varphi_1) = (\delta u^H, \delta u_1)$  in (2.18) and it follows from Cauchy's inequality and (1.3) that

$$\|\nabla \delta u^H + \nabla_{\mathbf{y}} \delta u_1\|_{L^2(\Omega \times Q)} \leq C\delta\beta \quad (2.22)$$

and it follows easily that

$$|\tilde{T}| < C\delta\beta^2. \quad (2.23)$$

Taking the  $\varepsilon_k \rightarrow 0$  limit in (2.13) noting that  $\lim_{\varepsilon_k \rightarrow 0} \delta u^{\varepsilon_k} = \delta u^H$  (weakly in  $H^1(\Omega)$ ) and recalling (2.16) gives

$$\delta\beta \times \lim_{\varepsilon_k \rightarrow 0} \int_{\Omega} p(\mathbf{x}, \mathbf{x}/\varepsilon_k) |\nabla u^{\varepsilon_k}|^2 d\mathbf{x} + O(\delta\beta^2) = - \int_{\Omega} f \delta u^H d\mathbf{x} - \int_{\partial\Omega_N} g \delta u^H ds. \quad (2.24)$$

Lemma 2.2 now follows immediately from (2.20), (2.23) and (2.24) and identifying like powers of  $\delta\beta$ .

### 3 Explicit lower bounds for aggregates of Schulgasser crystallites

In this section we derive the lower bound (1.22) for the microstructure consisting of Schulgasser crystallites embedded within a homogeneous matrix with unit thermal conductivity. The temperature field inside the unit period cell  $\Phi^i(\mathbf{y}) = w^i(\mathbf{y}) + \mathbf{y}_i$  is the solution of the local problem

$$\operatorname{div}_{\mathbf{y}} (A(\mathbf{y})(\nabla_{\mathbf{y}} w^i(\mathbf{y}) + \mathbf{e}^i)) = 0, \quad (3.1)$$

with  $w^i$   $Q$ -periodic and  $\int_Q w^i(\mathbf{y}) d\mathbf{y} = 0$ . For this microstructure  $A(\mathbf{y})$  is given by (1.20) for  $\mathbf{y}$  in  $B(\mathbf{y}^\ell, r_\ell)$  and  $A(\mathbf{y}) = I$  outside. Here we restrict  $\lambda_2$  to the interval  $(1/2, 1)$  and choose  $\lambda_1$  so that  $\lambda_1 = 1/(2\lambda_2 - 1)$ . A calculation shows that the solution  $\Phi^i(\mathbf{y})$  is given by

$$\Phi^i = \begin{cases} \mathbf{y}_i, & \mathbf{y} \in Q \setminus \cup_{\ell=1}^N B(\mathbf{y}^\ell, r_\ell), \\ r_\ell^{1-\alpha} |\mathbf{y} - \mathbf{y}^\ell|^{\alpha-1} (\mathbf{y}_i - \mathbf{y}^\ell) + \mathbf{y}_i, & \mathbf{y} \in B(\mathbf{y}^\ell, r_\ell) \end{cases}, \quad (3.2)$$

where  $\alpha = 2\lambda_2 - 1$ . The corrector matrix  $P(\mathbf{y})$  is given by

$$P(\mathbf{y}) = \begin{cases} I, & \mathbf{y} \in Q \setminus \cup_{\ell=1}^N B(\mathbf{y}^\ell, r_\ell), \\ r_\ell^{1-\alpha} |\mathbf{y} - \mathbf{y}^\ell|^{\alpha-1} (I + (\alpha - 1)\mathbf{n} \otimes \mathbf{n}), & \mathbf{y} \in B(\mathbf{y}^\ell, r_\ell) \end{cases}, \quad (3.3)$$

where  $\mathbf{n} = (\mathbf{y} - \mathbf{y}^\ell)/|\mathbf{y} - \mathbf{y}^\ell|$  for  $\mathbf{y} \in B(\mathbf{y}^\ell, r_\ell)$ . A direct calculation shows that

$$A^E = \int_Q A(\mathbf{y}) P(\mathbf{y}) d\mathbf{y} = I. \quad (3.4)$$

Next we provide the lower bound for  $\int_{\Omega} \int_Q |P(\mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} d\mathbf{x}$ . Note for any  $\eta$  in  $\mathbf{R}^3$  that  $P^T(\mathbf{y}) P(\mathbf{y}) \eta \cdot \eta = |P(\mathbf{y}) \eta|^2$  and the smallest eigenvalue  $\lambda(\mathbf{y})$  of  $P^T(\mathbf{y}) P(\mathbf{y})$  delivers the lower bound  $\lambda(\mathbf{y}) |\eta|^2 \leq |P(\mathbf{y}) \eta|^2$  and

$$\int_{\Omega} \int_Q \lambda(\mathbf{y})^{p/2} |\nabla u^H(\mathbf{x})|^p d\mathbf{y} d\mathbf{x} \leq \int_{\Omega} \int_Q |P(\mathbf{y}) \nabla u^H(\mathbf{x})|^p d\mathbf{y} d\mathbf{x}. \quad (3.5)$$

Calculation shows that

$$\lambda(\mathbf{y}) = \alpha^2 r_\ell^{2(1-\alpha)} |\mathbf{y} - \mathbf{y}^\ell|^{2(\alpha-1)} \quad (3.6)$$

for  $\mathbf{y} \in B(\mathbf{y}^\ell, r_\ell)$  and  $\lambda(\mathbf{y}) = 1$  for  $\mathbf{y} \in Q \setminus \cup_{\ell=1}^N B(\mathbf{y}^\ell, r_\ell)$ . The lower bound (1.22) follows upon substitution of (3.6) into (3.5).

## 4 Optimality of the lower bounds

Conditions are presented on  $f$  and  $A(\mathbf{y})$  for which the lower bound (1.14) is attained for a range of exponents  $2 < p < \hat{q}$ . We suppose as in Avellaneda and Lin [3] that  $\Omega$  is a  $C^{1,\alpha}$  domain ( $0 < \alpha \leq 1$ ) and suppose for  $0 < \gamma \leq 1$ ,  $0 < C$ , that  $A(\mathbf{y}) \in C^\gamma(\mathbf{R}^n)$  and  $\|A(\mathbf{y})\|_{C^\gamma(\mathbf{R}^n)} \leq C$ . We set  $A^{\varepsilon_k} = A(\mathbf{x}/\varepsilon_k)$ . For  $\delta > 0$  suppose  $2 \leq q \leq n + \delta$  and  $f \in L^q$  and set  $1/\hat{q} = 1/q - 1/(n + \delta)$ . Given these choices we consider the  $W_0^{1,2}(\Omega)$  solutions  $u^{\varepsilon_k}$  of

$$-\operatorname{div}(A^{\varepsilon_k}(\mathbf{x})\nabla u^{\varepsilon_k}) = f \quad \text{in } \Omega. \quad (4.1)$$

Theorem 4 of [3] shows that there exists a constant independent of  $\varepsilon_k$  for which

$$\|\nabla u^{\varepsilon_k}\|_{L^{\hat{q}}(\Omega)} \leq C\|f\|_{L^q(\Omega)} \quad (4.2)$$

holds for every  $\varepsilon_k > 0$ . Subject to these hypotheses it will be shown that the lower bound (1.14) is attained for  $p < \hat{q}$ .

Passing to a subsequence if necessary we start by considering the Young measure  $\nu$  associated with the sequence  $\{P(\mathbf{x}/\varepsilon_k)\nabla u^H(\mathbf{x})\}_{\varepsilon_k > 0}$ . Here  $\nu$  is represented by a family of probability measures  $\nu = \{\nu_{\mathbf{x}}\}_{\mathbf{x} \in \Omega}$  depending measurably on  $\mathbf{x}$ . We denote the set of continuous functions  $\varphi$  defined on  $\mathbf{R}^n$  such that  $\lim_{\eta \rightarrow \infty} \varphi(\eta) = 0$  by  $C_0(\mathbf{R}^n)$ . Elementary arguments show that

$$\langle \nu_{\mathbf{x}}, \varphi \rangle = \int_{\mathbf{R}^n} \varphi(\eta) d\nu_{\mathbf{x}}(\eta) = \int_Q \varphi(P(\mathbf{z})\nabla u^H(\mathbf{x})) d\mathbf{z}, \quad \text{a.e. } \mathbf{x} \in \Omega \quad (4.3)$$

for every  $\varphi$  in  $C_0(\mathbf{R}^n)$ . From corrector theory [17] there exists an exponent  $r \geq 1$  for which one has the strong convergence

$$\lim_{\varepsilon_k \rightarrow 0} \|\nabla u^{\varepsilon_k} - P(\mathbf{x}/\varepsilon_k)\nabla u^H\|_{L^r(\Omega)} = 0. \quad (4.4)$$

The strong convergence (4.4) shows that both sequences  $\{\nabla u^{\varepsilon_k}\}_{\varepsilon_k > 0}$  and  $\{P(\mathbf{x}/\varepsilon_k)\nabla u^H(\mathbf{x})\}_{\varepsilon_k > 0}$  share the same Young measure see for example Lemma 6.3 of [20]. From (4.2) it follows on passage to a subsequence if necessary that  $\{|\nabla u^{\varepsilon_k}|^p\}_{\varepsilon_k}$  is weakly convergent in  $L^1(\Omega)$  thus

$$\lim_{\varepsilon_k \rightarrow 0} \int_D |\nabla u^{\varepsilon_k}|^p d\mathbf{x} = \int_D \int_{\mathbf{R}^n} |\eta|^p d\nu_{\mathbf{x}}(\eta) d\mathbf{x} = \int_D \int_Q |P(\mathbf{z})\nabla u^H(\mathbf{x})|^p d\mathbf{z} d\mathbf{x}, \quad (4.5)$$

and optimality follows. Last, it follows immediately from Proposition 6.5 of [20] that for every Caratheodory function  $\psi(\mathbf{x}, \eta)$  satisfying the growth condition (1.25) that (on passage to a subsequence if necessary)

$$\lim_{\varepsilon_k \rightarrow 0} \int_D \psi(\mathbf{x}, \nabla u^{\varepsilon_k}) d\mathbf{x} = \int_D \int_{\mathbf{R}^n} \psi(\mathbf{x}, \eta) d\nu_{\mathbf{x}}(\eta) d\mathbf{x} \quad (4.6)$$

and (1.26) follows since (4.3) implies that

$$\int_D \int_{\mathbf{R}^n} \psi(\mathbf{x}, \eta) d\nu_{\mathbf{x}}(\eta) d\mathbf{x} = \int_D \int_Q \psi(\mathbf{x}, P(\mathbf{z})\nabla u^H(\mathbf{x})) d\mathbf{z} d\mathbf{x}. \quad (4.7)$$

## 5 Acknowledgments

This research effort is sponsored by NSF through grant DMS-0406374 and by the Air Force Office of Scientific Research, Air Force Material Command USAF, under grant numbers F49620-02-1-0041 and FA9550-05-1-0008. The US Government is authorized to reproduce and distribute reprints for governmental purposes notwithstanding any copyright notation thereon. The views and conclusions herein are those of the authors and should not be interpreted as necessarily representing the official policies or endorsements, either expressed or implied of the Air Force Office of Scientific Research or the US Government.

## References

- [1] G. Allaire (1992), Homogenization and two-scale convergence, *SIAM J. Math. Anal.*, **23**, pp. 1482–1518.
- [2] G. Allaire and M. Briane (1996), Multi-scale convergence and reiterated homogenization, *Proc. Roy. Soc. Edinburgh*, **126A**, pp. 297–342.
- [3] M. Avellaneda and F.H. Lin (1987), Compactness methods in the theory of homogenization. *Comm. Pure Appl. Math.*, **40**, pp. 806–847.
- [4] A. Bensoussan, J.L. Lions and G. Papanicolaou, *Asymptotic Analysis for Periodic Structures*. Studies in Mathematics and its Applications, 5, North-Holland, Amsterdam, 1978.
- [5] D. Cioranescu, A. Damlamian and G. Griso (2002), Periodic unfolding and homogenization, *C. R. Acad. Sci. Paris, Ser.*, **I 335**, pp. 99–104
- [6] J.H. Gosse and S. Christensen (2001), Strain invariant failure criteria for polymers in composite materials, *AIAA 2001-1184*, p. 11.
- [7] C. E. Gutierrez and I. Peral (2001), A harmonic analysis theorem and applications to homogenization, *Indiana University Mathematics Journal*, **50**, pp. 1651–1674.
- [8] A. Kelly and N.H. Macmillan, *Strong Solids*. Monographs on the Physics and Chemistry of Materials. Clarendon Press, Oxford, 1986.
- [9] Y.Y. Li and M. Vogelius (2000), Gradient estimates for solutions to divergence form elliptic equations with discontinuous coefficients. *Arch. Rational Mech. Anal.* **153**, pp. 91-151.
- [10] Y.Y. Li and L. Nirenberg (2003), Estimates for elliptic systems from composite material. *Comm. Pure Appl. Math.* **56**, pp. 892–925.
- [11] R. Lipton (2003), Assessment of the local stress state through macroscopic variables, *R. Soc. Lond. Philos. Trans. Ser. A Math. Phys. Eng. Sci.*, **361**, pp. 921 – 946.
- [12] R. Lipton (2004), Homogenization theory and the assessment of extreme field values in composites with random microstructure, *SIAM J. Applied Mathematics* **65**, pp. 475–493.

- [13] R. Lipton (2003), On stress constrained G closure and relaxation of structural design problems, *Quarterly of Applied Math.*, **LXII**, pp. 295–321.
- [14] D. Luckkassen, G. Nguetseng and P. Wall (2002), Two-scale convergence, *Int. J. of Pure and Appl. Math.*, **2**, pp.35–86.
- [15] N. Meyers (1963), An  $L^p$  estimate for the gradient of solutions of second order elliptic divergence form equations, *Ann. Sc. Norm. Sup. Pisa Serie III* **XVII**, pp. 189–206.
- [16] G.W. Milton (1986), Modeling the properties of composites by laminates, in *Homogenization and Effective Moduli of Materials and Media*, Ericksen, Kinderlehrer, Kohn, Lions, eds., IMA Volumes in Mathematics and its Applications, Volume 1, Springer Verlag, Heidelberg.
- [17] F. Murat and L. Tartar (1978), H-convergence, *Séminaire d'Analyse Fonctionnelle et Numérique de l'Université d'Alger*. Mimeographed notes. English translation: *Topics in the Mathematical Modeling of Composite Materials* (eds A. Cherkhaev and R. V. Kohn; Birkhäuser, Boston 1997) 2143.
- [18] G. Nguetseng (1989), A general convergence result for a functional related to the theory of homogenization, *SIAM J. Math. Anal.*, **20**, pp. 608–623.
- [19] N.J. Pagano and F.G. Yuan (2000), On the significance of effective modulus theory (homogenization) in composite laminate mechanics, *Comp. Sci. Tech.*, **60**, pp. 2471–2488.
- [20] P. Pedregal, *Parametrized Measures and Variational Principles*. Birkhäuser, Berlin, 1997.
- [21] P. Raghaven, S. Moorthy, S. Ghosh and N.J. Pagano (2001), Revisiting the composite laminate problem with an adaptive multi-level computational model, *Comp. Sci. Tech.*, **61**, pp. 1017–1040.
- [22] K. Schulgasser (1983), Sphere assemblage model for polycrystals and symmetric materials, *Journal of Applied Physics*, **54**, pp. 1380–1382.
- [23] B. Schweizer (2000), Uniform estimates in two periodic problems, *Comm. Pure Appl. Math.*, **53**, pp. 1153–1176.